

2217 LANGDON FARM RD. * CINCINNATI, OHIO 45237-4792
Ph: (513) 631-4270 * FAX: (513) 366-4444

PRODUCT INFORMATION SHEET

CUSTOMER: CUSTOMER SERVICE

DATE:

LOCATION:

REPRESENTATIVE:

PRODUCT NO.: 039355/61062

DESCRIPTION: W/R Conductive Coating

SPECIFICATION

VISCOSITY: 14-16 Sec(#3 Zahn Cup)

LBS/GAL: 8.81

% SOLIDS (WGT): 33.0-34.0

VOC: 3.23 LBS/GAL

% SOLIDS (VOLUME): 27.0-28.0

COLOR(S): Black Only

GLOSS: 10-20 Units(60 Degree Meter)

THEORETICAL COVERAGE: 442 FT²/GAL @ 1.0 MIL(S) (NO LOSS)

APPLICATION

METHOD: Spray

RECOMMENDED BUILD: 0.9-1.2 MIL(S) (DRY).

APPLICATION VISCOSITY: 14-16 Sec(#3 Zahn Cup)

RECOMMENDED REDUCTION: None

WITH: None

COMPATIBLE FAST SOLVENT:

COMPATIBLE SLOW SOLVENT: Water

OTHER RECOMMENDATIONS:

..Mix 4 parts 39355 to 1 part 61062.

SUBSTRATE

SURFACE TO BE COATED: Plastic & Metal

RECOAT SCHEDULE:

APPLY OVER UNDER

Clean, properly prepared surface

DRY SCHEDULE

AIR DRY SET-TO-TOUCH:

TACK FREE:

HANDLE:

PACK PARTS: 24 Hours

HEAT CURE FLASH TIME: 10 Minutes

SCHEDULE: 15

@ 220 F

DEG. F

TYPICAL PERFORMANCE:

Specs pertain to admixed material mix 4 parts 39355 to 1 part.61062 When used as a primer on plastic. parts, topcoat may be applied electrostatically

PROD. NO. 039355/61062

SHOULD BE USED WITHIN 6 Months

FROM DATE OF

DISCLAIMER

ANY RECOMMENDATIONS WE MAKE WITH RESPECT TO OUR PRODUCTS ARE BASED UPON MANY YEARS OF EXPERIENCE IN THE MANUFACTURE OF INDUSTRIAL PRODUCT FINISHES AND ON TESTS WE DEVELOPED AND BELIEVE TO BE RELIABLE: HOWEVER, WE DO NOT ASSUME ANY RESPONSIBILITY FOR ANY OF THOSE RECOMMENDATIONS OR ANY SUGGESTIONS MADE BY OUR REPRESENTATIVES. THE USE AND APPLICATION OF OUR PRODUCTS IS BEYOND OUR CONTROL AND **WE MAKE NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE**, AND WE DISCLAIM RESPONSIBILITY OR FITNESS FOR A PARTICULAR PURPOSE, AND WE DISCLAIM RESPONSIBILITY FOR THE RESULTS, INCLUDING DAMAGE