

2217 LANGDON FARM RD. * CINCINNATI, OHIO 45237-4792
Ph: (513) 631-4270 * FAX: (513) 366-4444

PRODUCT INFORMATION SHEET

CUSTOMER: _____ DATE: _____
LOCATION: _____ REPRESENTATIVE: _____
PRODUCT NO.: 039856/61062 DESCRIPTION: W/R EPOXY

SPECIFICATION

VISCOSITY: 67-72 KREB UNITS LBS/GAL: 11.10
% SOLIDS (WGT): 51.5-52.5 VOC: 2.36 LBS/GAL
% SOLIDS (VOLUME): 36.0-37.0 COLOR(S): MATCH STD.
GLOSS: 20-30 UNITS (60 DEG. METER)
THEORETICAL COVERAGE: 294 FT²/GAL @ 2.0 MIL(S) (NO LOSS)

APPLICATION

METHOD: SPRAY RECOMMENDED BUILD: 1.8-2.2 MIL(S) (DRY).
APPLICATION VISCOSITY: 67-72 KREB UNIT
RECOMMENDED REDUCTION: NONE WITH: NONE
COMPATIBLE FAST SOLVENT: WATER COMPATIBLE SLOW SOLVENT: WATER
OTHER RECOMMENDATIONS:

SUBSTRATE

SURFACE TO BE COATED: STEEL RECOAT SCHEDULE:
APPLY OVER UNDER CLEAN, PROPERLY PREPARED SURFACE

DRY SCHEDULE

AIR DRY SET-TO-TOUCH: 30 MINUTES TACK FREE: 1-2 HOURS HANDLE: _____ PACK PARTS:
HEAT CURE FLASH TIME: _____ SCHEDULE: _____ @ _____ DEG. F

TYPICAL PERFORMANCE:

PROD. NO. 039856/61062 SHOULD BE USED WITHIN 6 MONTHS FROM DATE OF

DISCLAIMER

ANY RECOMMENDATIONS WE MAKE WITH RESPECT TO OUR PRODUCTS ARE BASED UPON MANY YEARS OF EXPERIENCE IN THE MANUFACTURE OF INDUSTRIAL PRODUCT FINISHES AND ON TESTS WE DEVELOPED AND BELIEVE TO BE RELIABLE: HOWEVER, WE DO NOT ASSUME ANY RESPONSIBILITY FOR ANY OF THOSE RECOMMENDATIONS OR ANY SUGGESTIONS MADE BY OUR REPRESENTATIVES. THE USE AND APPLICATION OF OUR PRODUCTS IS BEYOND OUR CONTROL AND **WE MAKE NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE**, AND WE DISCLAIM RESPONSIBILITY OR FITNESS FOR A PARTICULAR PURPOSE, AND WE DISCLAIM RESPONSIBILITY FOR THE RESULTS, INCLUDING DAMAGE