

2217 LANGDON FARM RD. * CINCINNATI, OHIO 45237-4792
Ph: (513) 631-4270 * FAX: (513) 366-4444

PRODUCT INFORMATION SHEET

CUSTOMER:

DATE:

LOCATION:

REPRESENTATIVE:

PRODUCT NO.: 040424/61092

DESCRIPTION: Gloss Urethane

SPECIFICATION

VISCOSITY: 30-35 sec. (#2 Zahn Cup)

LBS/GAL: 8.23

% SOLIDS (WGT): 48.0-49.0

VOC: 3.34 LBS/GAL

% SOLIDS (VOLUME): 40.0-41.0

COLOR(S): Match Std.

GLOSS: 85-95 units (60 deg meter)

THEORETICAL COVERAGE: 649 FT²/GAL @ 1.0 MIL(S) (NO LOSS)

APPLICATION

METHOD: spray

RECOMMENDED BUILD: 1.0-1.2 MIL(S) (DRY).

APPLICATION VISCOSITY: 30-35 sec (#2 Zahn Cup)

RECOMMENDED REDUCTION: as needed

WITH: acetone.

COMPATIBLE FAST SOLVENT: toluene

COMPATIBLE SLOW SOLVENT: xylene

OTHER RECOMMENDATIONS:

.All specs pertain to admixed material..Blend 4 parts (by volume) 40424 to 1 part.(by volume) 61092.

SUBSTRATE

SURFACE TO BE COATED: steel

RECOAT SCHEDULE:

APPLY OVER UNDER 404230gray primer

DRY SCHEDULE

AIR DRY SET-TO-TOUCH: 40 min.

TACK FREE: 4 hours

HANDLE: 5 hours

PACK PARTS: 24 hours

HEAT CURE FLASH TIME:

SCHEDULE:

@

DEG. F

TYPICAL PERFORMANCE:

.Passed 200 hours salt spray over 40423.Gray Primer when sprayed on B1000..Passed 300 hours QUV.

PROD. NO. 040424/61092

SHOULD BE USED WITHIN 6 months

FROM DATE OF

DISCLAIMER

ANY RECOMMENDATIONS WE MAKE WITH RESPECT TO OUR PRODUCTS ARE BASED UPON MANY YEARS OF EXPERIENCE IN THE MANUFACTURE OF INDUSTRIAL PRODUCT FINISHES AND ON TESTS WE DEVELOPED AND BELIEVE TO BE RELIABLE: HOWEVER, WE DO NOT ASSUME ANY RESPONSIBILITY FOR ANY OF THOSE RECOMMENDATIONS OR ANY SUGGESTIONS MADE BY OUR REPRESENTATIVES. THE USE AND APPLICATION OF OUR PRODUCTS IS BEYOND OUR CONTROL AND **WE MAKE NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE**, AND WE DISCLAIM RESPONSIBILITY OR FITNESS FOR A PARTICULAR PURPOSE, AND WE DISCLAIM RESPONSIBILITY FOR THE RESULTS, INCLUDING DAMAGE